

## **Addenda October 1, 2018**

### **Port of Brookings Dock Pile Repair/Replacement**

Several good questions have been asked by interested and qualified potential bidders in recent days. In conformance with Section item 3.3, Bid Doc #3 (ADDED INSTRUCTION TO BIDDERS), the following addenda are provided, in an effort to answer these questions (answers in caps and emboldened):

1. What type of hoops and/or caps are being requested? **ALL PROPOSED HOOPS AND CAPS WILL BE ACCEPTABLE FOR BID PURPOSES. HOWEVER, A COMPARISON OF THE QUALITY AND FUNCTIONALITY OF HOOPS AND/OR CAPS LISTED IN PROPOSALS WILL BE MADE. FURTHER QUALIFICATION MAY BE REQUESTED FROM BIDDERS BY THE PORT AFTER OCTOBER 10<sup>TH</sup> BUT PRIOR TO SELECTION. THE HOOPS AND CAPS LOCATED ALONG DOCK "H" ARE PREFERRED. A PHOTO OF ONE OF THESE HOOPS IS ON THE PORT OF BROOKINGS HARBOR WEBSITE.**
2. How many hoops and/or caps will be needed? **THE BID REQUIRES ONE HOOP AND ONE CAP FOR EACH OF THE 92 (NINETY-TWO) PILES.**
3. Where exactly will the piles be placed? **THE PILES WILL APPROXIMATELY BE PLACED AS SHOWN IN THE DRAWING ATTACHED TO BID DOC #5. MORE PRECISE LOCATIONS WILL BE DETERMINED AFTER BIDDER SELECTION, DURING THE WORKPLAN DEVELOPMENT PERIOD. PILES WILL BE APPROXIMATELY EVENLY DISTRIBUTED AMONG DOCKS B THROUGH H, MORE HEAVILY WEIGHTED TOWARDS THE GREATER DEPTHS AT EACH DOCK.**
4. Is all or just a part of piles surfaces to be coated? **FOR THE PURPOSES OF THIS PROPOSAL REQUEST, THE BIDDER SHOULD PROPOSE THAT THE ENTIRE SURFACE OF EACH PILE IS COATED.**
5. What kind of coating is to be used? **AN APPROVED (DEVRON 261 QC) IS CITED IN THE RFP, BUT EQUIVALENT COATINGS MAY BE PROPOSED. THE COATING PROPOSED MUST NOT BE A CHRONIC HAZARD TO AQUATIC LIFE ENVIRONMENTS, FLAMMABLE OR CAUSTIC (WHEN CURED). A COPY OF AN ACCEPTABLE PRODUCT (DEVRON) IS PLACED ON THE PORT OF BROOKINGS HARBOR WEBSITE.**

**PRODUCT DESCRIPTION**

A high performance, chemically cured, epoxy primer/intermediate for steel.

**INTENDED USES**

Designed for use in aggressive industrial environments and the process industries and offers excellent low temperature cure characteristics and resistance to acids, bases and solvents.

Especially formulated for use as a fast recoat system for quick turn around for piling repair or in fabrication shops doing work for industries such as pulp and paper, water and waste water, chemical processing, petrochemical, power and cogeneration, etc.

**PRACTICAL INFORMATION FOR DEVRAN 261QC**

<b>Color</b>	White, Black, Gray
<b>Gloss Level</b>	Semi-gloss
<b>Volume Solids</b>	70% ± 2%
<b>Typical Thickness</b>	4-6 mils (100-150 microns) dry equivalent to 5.7-8.6 mils (143-214 microns) wet
<b>Theoretical Coverage</b>	225 sq ft/US gallon at 5 mils d.f.t and stated volume solids 5.60 m <sup>2</sup> /liter at 125 microns d.f.t and stated volume solids
<b>Practical Coverage</b>	Allow appropriate loss factors
<b>Method of Application</b>	Airless Spray, Roller, Air Spray, Brush

**Drying Time**

Temperature	Touch Dry	Hard Dry	Overcoating interval with self	
			Minimum	Maximum
32°F (0°C)	**	15 hours	4 hours	10 days <sup>2</sup>
41°F (5°C)	**	6 hours	3 hours	6 days <sup>2</sup>
77°F (25°C)	**	3 hours	3 hours	4 days <sup>2</sup>

\* Not applicable

<sup>2</sup> Overcoating intervals will be reduced where certain topcoats are used. See Product Characteristics section for further details.

**REGULATORY DATA**

<b>Flash Point</b>	Part A 81°F (27°C); Part B 81°F (27°C); Mixed 81°F (27°C)
<b>Product Weight</b>	11.8 lb/gal (1.42 kg/l)
<b>VOC</b>	2.23 lb/gal (268 g/l) EPA Method 24
See Product Characteristics section.	

## SURFACE PREPARATION

Surfaces must be dry, clean, free of oil, grease, form release agents, curing compounds, laitance, other foreign matter and be structurally sound. Remove all loose paint, mortar spatter, mill scale, and rust.

### New Surfaces

#### Steel:

Abrasive blast to minimum SSPC-SP10 or ISO8501-1:2007 Sa2½. The blast profile should be jagged rather than "peened" and between 1.5 to 2.5 mils (38-62 microns). After blasting, vacuum or blow off all abrasive dust and ensure surface remains clean before painting.

## APPLICATION

<b>Mixing</b>	Material is supplied in two containers as a unit. Always mix a complete unit in the proportions supplied. Once the unit has been mixed it must be used within the working pot life specified.		
	(1) Agitate Base (Part A) with a power agitator. (2) Combine entire contents of Curing Agent (Part B) with Base (Part A) and mix thoroughly with power agitator.		
<b>Mix Ratio</b>	2 part(s) : 1 part(s) by volume		
<b>Working Pot Life</b>	32°F (0°C)	41°F (5°C)	77°F (25°C)
	1 hour	1 hour	1 hour
<b>Airless Spray</b>	Recommended	Tip Range 21-25 thou (0.53-0.63 mm) Total output fluid pressure at spray tip not less than 3000 psi (211 kg/cm <sup>2</sup> ) See Product Characteristics section.	
<b>Thinner</b>	T-5 Thinner	See Product Characteristics section.	
<b>Cleaner</b>	T-10 Thinner		
<b>Work Stoppages</b>	Do not allow material to remain in hoses, gun or spray equipment. Thoroughly flush all equipment with T-10 Thinner. Once units of paint have been mixed they should not be resealed and it is advised that after prolonged stoppages work recommences with freshly mixed units.		
<b>Clean Up</b>	Clean all equipment immediately after use with T-10 Thinner. It is good working practice to periodically flush out spray equipment during the course of the working day. Frequency of cleaning will depend upon amount sprayed, temperature and elapsed time, including any delays. All surplus material and empty containers should be disposed of in accordance with appropriate regional regulations/legislation.		

**PRODUCT CHARACTERISTICS**

**Advantages:**

- Excellent low temperature cure even down to 0°F (-18°C)
- Fast recoat time

Thinning is not normally required or desired, however, at lower temperatures, small amounts (5% or less by volume) of T-5 thinner can be added depending on local VOC and air quality regulations.

For airless spray application: Ideally, fluid hoses should not be less than 3/8" ID and not longer than 50 feet to obtain optimum results. Longer hose length may require an increase in pump capacity, pressure, and/or thinning.

In common with all epoxies, Devran 261QC will chalk and discolor on exterior exposure. However, these phenomena are not detrimental to anti-corrosive performance.

Devran 261QC may yellow during application and cure if exposed to the combustion by-products of improperly vented fossil fuel burning heaters.

Where a durable cosmetic finish with good gloss and color retention is required, overcoat with recommended topcoats.

Where Devran 261QC is to be overcoated with Devthane 378 or 379 finish coats, the following overcoating intervals will apply,

	Minimum	Maximum
32°F (0°C)	4 hours	1 day
41°F (5°C)	3 hours	1 day
77°F (25°C)	2 hours	1 day

Where Devran 261QC is to be overcoated with Devthane 389, 359 and 349QC, the following overcoating intervals will apply,

	Minimum	Maximum
32°F (0°C)	4 hours	7 days
41°F (5°C)	3 hours	4 days
77°F (25°C)	2 hours	2 days

Devran 261QC may be tinted with industrial colorants; contact International Paint for further information. Add colorants only to the base portion and mix thoroughly before adding the converter portion.

Note: VOC values are typical and are provided for guidance purpose only. These may be subject to variation depending on factors such as differences in color and normal manufacturing tolerances.

Low molecular weight reactive additives, which will form part of the film during normal ambient cure conditions, will also effect VOC values determined using EPA Method 24.

**SYSTEMS COMPATIBILITY**

The following primers are recommended for Devran 261QC:

Cathacoat 302H	Cathacoat 302HA
Cathacoat 302HB	Cathacoat 304L
Cathacoat 304V	

The following topcoats are recommended:-

Devthane 349QC	Devthane 359
Devthane 359H	Devthane 378
Devthane 379	Devthane 389

**ADDITIONAL INFORMATION**

Further information regarding industry standards, terms and abbreviations used in this data sheet can be found in the following documents available at [www.international-pc.com](http://www.international-pc.com)

- Definitions & Abbreviations
- Surface Preparation
- Paint Application
- Theoretical & Practical Coverage

Individual copies of these information sections are available upon request.

**SAFETY PRECAUTIONS**

This product is intended for use only by professional applicators in industrial situations in accordance with the advice given on this sheet, the Material Safety Data Sheet and the container(s), and should not be used without reference to the Material Safety Data Sheet (MSDS) which International Protective Coatings has provided to its customers.

All work involving the application and use of this product should be performed in compliance with all relevant national, Health, Safety & Environmental standards and regulations.

In the event welding or flame cutting is performed on metal coated with this product, dust and fumes will be emitted which will require the use of appropriate personal protective equipment and adequate local exhaust ventilation.

If in doubt regarding the suitability of use of this product, consult International Protective Coatings for further advice.

<b>PACK SIZE</b>	Unit Size	Part A		Part B	
		Vol	Pack	Vol	Pack
	3 US gal	2 US gal	5 US gal	1 US gal	1 US gal
For availability of other pack sizes contact International Protective Coatings					
<b>SHIPPING WEIGHT</b>	Unit Size	Part A	Part B		
	3 US gal	27.9 lb	13.9 lb		
<b>STORAGE</b>	Shelf Life	24 months minimum at 77°F (25°C). Subject to re-inspection thereafter. Store in dry, shaded conditions away from sources of heat and ignition.			


**Disclaimer**

*The information in this data sheet is not intended to be exhaustive. Any person using the product for any purpose other than that specifically recommended in this data sheet without first obtaining written confirmation from us as to the suitability of the product for the intended purpose does so at their own risk. All advice given or statements made about the product (whether in this data sheet or otherwise) is correct to the best of our knowledge but we have no control over the quality or the condition of the substrate or the many factors affecting the use and application of the product. THEREFORE, UNLESS WE SPECIFICALLY AGREE IN WRITING TO DO SO, WE DO NOT ACCEPT ANY LIABILITY AT ALL FOR THE PERFORMANCE OF THE PRODUCT OR FOR (SUBJECT TO THE MAXIMUM EXTENT PERMITTED BY LAW) ANY LOSS OR DAMAGE ARISING OUT OF THE USE OF THE PRODUCT. WE HEREBY DISCLAIM ANY WARRANTIES OR REPRESENTATIONS, EXPRESS OR IMPLIED, BY OPERATION OF LAW OR OTHERWISE, INCLUDING, WITHOUT LIMITATION, ANY IMPLIED WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. All products supplied and technical advice given are subject to our Conditions of Sale. You should request a copy of this document and review it carefully. The information contained in this data sheet is liable to modification from time to time in the light of experience and our policy of continuous development. It is the user's responsibility to check with their local International Paint representative that this data sheet is current prior to using the product.*

Copyright © AkzoNobel, 7/19/2011

 Copyright © AkzoNobel, 7/19/2011

[www.international-pc.com](http://www.international-pc.com)



**THE PHOTO ABOVE IS OF AN EXISTING HOOP AT THE PORT OF BROOKINGS HARBOR. THIS TYPE OF HOOP IS PREFERRED. THE BIDDER IS EXPECTED TO DISTINGUISH INSTALLATION OF DOCK-END HOOPS FROM THOSE INSTALLED ALONGSIDE DOCKS.**